

# HM 2471 / GPO-3

## POLYESTER GLASS LAMINATE

### Material description

HM 2471-GPO3 is a glass mat reinforced plastic with excellent arc and creepage-path properties. The material has a defined (UL listed).burning behaviour.

### Conformities

RoHS, REACH

Physical properties	Test method	Value	Unit
Density	DIN EN ISO 1183-1	1.85	g/cm <sup>3</sup>
Water absorbtion	DIN 53495	60	mg
Sliding friction		○	
Abrasion resistance		○	

Mechanical properties	Test method	Value	Unit
Tensile strength	DIN 53455	60	MPa
Modulus of elasticity from bending test	ISO 178	10000	MPa
Bending stress at fracture perpendicular to the layer direction	ISO 178	130	MPa
Shear strength parallel to the layer direction	VDE 0318/2	20	MPa
Notched impact strength (Charpy) parallel to the layer direction	DIN 53453	40	kJ/m <sup>2</sup>
Compressive strength parallel to the direction of layering	DIN 53454	140	MPa
Compressive strength perpendicular to the layer direction	DIN 53454	200	MPa

Thermal properties	Test method	Value	Unit
Coefficient of linear expansion	VDE 0304/2	20-30	10 <sup>-6</sup> *K <sup>-1</sup>
Thermal endurance	VDE 0304/2	155	°C
Flammability	UL 94, 3 mm	V0	

Electrical properties	Test method	Value	Unit
Dielectric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	9	kV/mm
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	35	kV
Comparative tracking index (CTI)	IEC 60112	600	CTI

These technical data have been determined as average values by our suppliers from many individual measurements. In all measurements, the test specimens were tested in the dry state. We pass on the data with reservation. The table does not claim to be complete or correct. Material technology is subject to constant further development. No rights or guarantees can be derived from it. Own tests are necessary because the environmental and operating conditions (humidity, temperature, mechanical forces, radiation and chemicals, etc.) set limits in the application.